

**MGPL TECHNICAL SPECIFICATIONS : GC-90**

<u>Property</u>	<u>Test Method</u>	<u>Unit</u>	<u>Test Result</u>
Material			Polypropylene Slit Woven
Construction Weave			24x10
Weight	ASTM D-5261	GSM	90
Wide width strength	ASTM D-4595	Kn/m	19
Wide width strength	ASTM D-4595	Kn/m	13
Elongation	ASTM D-4595	%	15
Elongation	ASTM D-4595	%	13
Grab Tensile Strength (MD)	ASTM D-4632	LBS	140
Grab Tensile Strength (CD)	ASTM D-4632	LBS	80
Grab Elongation (MD)	ASTM D-4632	%	15
Grab Elongation (CD)	ASTM D-4632	%	14
Trapezoidal Tear (MD)	ASTM D-4533	LBS	65
Trapezoidal Tear (CD)	ASTM D-4533	LBS	45
CBR Puncture	ASTM D-6241	LBS	500
Permittivity	ASTM D-4491	1/Sec	0.160
Water Flow	ASTM D-4491	L/M <sup>2</sup> /Sec	8.6
UV Resistance	ASTM D-4355	%	80% (@500 Hrs UV Exposure)

**MACFIL GLOBAL PVT LTD**

Plot No 1, Survey No. 76, Makhiyav-Hirapur Road, Village- Makhiyav, Tal- Sanand, Dist – Ahmedabad, Gujarat (INDIA) – 382110

[info@macfilglobal.com](mailto:info@macfilglobal.com) | [www.macfilglobal.com](http://www.macfilglobal.com)